

Deflectography results fro the A2 between Carrickfergus and the Dual Carriageway at Factory near Seapark. Performed in April 2005

Road Name	Direction	Chainage (m)		Average Measured Deflection	Residual Life (Years)	Recommended ovelay to Achieve 20 year life (mm)
		Start	Finish			
A2	NB	0	99	0.435	2.3	135
A2	NB	100	199	0.360	3.42	106
A2	NB	200	299	0.447	1.89	140
A2	NB	300	399	0.385	3.1	117
A2	NB	400	499	0.385	3.42	117
A2	NB	500	599	0.472	1.71	148
A2	NB	600	699	0.360	3.42	106
A2	NB	700	799	0.335	4.18	95
A2	NB	800	899	0.535	1.02	166
A2	NB	900	999	0.422	2.3	131
A2	NB	1000	1099	0.410	2.54	126
A2	NB	1100	1199	0.560	0.72	173
A2	NB	1200	1299	0.435	2.09	135
A2	NB	1300	1399	0.548	0.81	170
A2	NB	1400	1499	0.385	3.1	117
A2	NB	1500	1599	0.435	1.89	135
A2	NB	1600	1699	0.500	1.24	156
A2	NB	1700	1799	0.564	0.69	174
A2	NB	1800	1899	0.325	4.98	90
A2	NB	1900	1999	0.340	4.46	97
A2	NB	2000	2099	0.328	5.41	92
A2	NB	2100	2199	0.367	3.94	109
A2	NB	2200	2246	0.291	7.34	73

Notes: NB equals North Bound.