

Deflectography results fro the A2 between Carrickfergus and the Dual Carriageway at Factory near Seapark. Performed in April 2005

Road Name	Direction	Chainage (m)		Average Measured Deflection	Residual Life (Years)	Recommended ovelay to Achieve 20 year life (mm)
		Start	Finish			
A2	WB	0	99	0.459	1.89	144
A2	WB	100	199	0.347	4.60	101
A2	WB	200	299	0.252	10.34	49
A2	WB	300	399	0.320	4.11	88
A2	WB	400	499	0.292	7.24	74
A2	WB	500	599	0.278	4.10	66
A2	WB	600	699	0.255	4.10	52
A2	WB	700	799	0.267	0.76	59
A2	WB	800	899	0.232	7.08	40
A2	WB	900	999	0.290	0.92(?)	73
A2	WB	1000	1099	0.255	2.86	52
A2	WB	1100	1199	0.344	2.23	100
A2	WB	1200	1299	0.306	4.50	81
A2	WB	1300	1399	0.217	12.68	40
A2	WB	1400	1499	0.268	6.10	60
A2	WB	1500	1599	0.268	7.07	60
A2	WB	1600	1699	0.268	7.07	60
A2	WB	1700	1799	0.230	10.93	40
A2	WB	1800	1899	0.268	6.07	60
A2	WB	1900	1999	0.231	10.84	40
A2	WB	2000	2099	0.181	20.04	40
A2	WB	2100	2199	0.169	23.69	0
A2	WB	2200	2299	0.258	7.94	53
A2	WB	2300	2399	0.271	6.82	62
A2	WB	2400	2445	0.284	5.84	69

Notes: WB equals West Bound.